


The Super D-Gun™ process is an advanced thermal spray method that yields unique coatings with extraordinary wear and mechanical properties. Super D-Gun particle velocities are higher than traditional thermal spray processes (up to 3000 ft/sec or 900 m/sec). The resulting coatings have a characteristic thermal spray lamellar microstructure, but with a density that is very close to theoretical.

The Coatings

The extremely high particle velocities of the Super D-Gun process result in significant advances in coating properties over those of other thermal spray coatings, even over comparable conventional detonation gun coatings. For example, using a modified Ollard test, tensile bond strengths in excess of 30,000 psi (210 MPa) have been measured. Abrasive wear, erosive wear, and impact fretting wear have all been substantially improved over comparable conventional detonation gun coatings as well as other thermally sprayed coatings.

Inherent in most thermally sprayed coatings is a residual tensile stress which may substantially reduce the strain-to-fracture of such coatings. This, in turn, may lead to a significant reduction in the fatigue characteristics of coated components. For many of the Super D-Gun coatings, however, a residual compressive stress, in some cases as high as 50,000 psi (340 MPa), is achieved. As a result, the strain-to-fracture may be as high as 0.8%, while for most conventional detonation gun coatings it may be less than 0.4%. [A strain of 0.8% corresponds to a stress in a coated steel part of 240,000 psi (1,600 MPa) in the part itself.]



Schematic of the Super D-Gun™ Process

Even lower values are common to most plasma sprayed and other thermally sprayed coatings. The high strain tolerance of coated components permits greater load carrying capacity in both shock and severe service environments. This high strain-to-fracture also strongly influences the effect of Super D-Gun coatings on the fatigue strength of substrates. In some cases, no fatigue debit is measurable. In other cases, the fatigue debit is significantly lower than experienced with conventional thermal spray coatings.

The as-deposited surface roughness of Super D-Gun coatings vary with the type of coatings from less than 100 to over 200 $\mu\text{in Ra}$ (2.5 to 5.0 $\mu\text{m Ra}$). Although for many applications a coating is used as-deposited, most are either ground or ground and lapped. Because of the very high density and cohesive strength of Super D-Gun coatings, pit-free surface finishes as low as 0.4 $\mu\text{in Ra}$ (0.01 $\mu\text{m Ra}$) can be achieved.

Typical coating thicknesses range from about 0.002 to 0.020 inches (0.05 to 0.5mm), but both thicker and thinner coatings are used on occasion, depending on the specific application. Because of the unique control of residual stress, Super D-Gun coatings can frequently be used at much greater thicknesses than can be achieved with other thermally sprayed coatings.

The Process

The Super D-Gun process employs a D-Gun™, as illustrated in the figure. Carefully measured gases, usually consisting of oxygen and acetylene-fuel gas mixture, are fed into the barrel of the gun along with a charge of fine powder. The gas is ignited and the resulting detonation wave heats and accelerates the powder as it moves down the barrel. The gas velocity and density are much higher than in a conventional detonation gun. The powder is entrained for a sufficient distance for it to be accelerated to its extraordinary velocity. A pulse of

nitrogen gas is used to purge the barrel after each detonation. The process is repeated many times per second. Each detonation results in the deposition of a circle (disk) of coating material a few microns thick. The total coating consists of many overlapping disks. Precise, fully automated, disk placement results in a very uniform coating

thickness and a relatively smooth, planar surface.

The Super D-Gun process is called "line-of-sight" because the gun must be able to "see" the area to be coated. This characteristic is true of all thermal spray coatings. For other thermal spray coatings, the best coating properties are

achieved when the angle of deposition is close to 90 degrees to the surface. As the angle of deposition deviates from the optimum, the properties of the coatings begin to degrade. Because of the extremely high powder velocity of the Super D-Gun process, however, little degradation in properties is noted down to at least 45 degrees.

More Information

Complete information on specific coatings and design considerations are available from technical field representatives. Contact one of these locations for the name of your area representative.

United States

Praxair Surface Technologies, Inc.
1500 Polco Street
Indianapolis, IN 46224
Phone: 317 240 2500
Fax: 317 240 2426

Praxair Surface Technologies, Inc.
1234 Atlantic Street
North Kansas City, MO 64116
Phone: 816 556 4600
Fax: 816 556 4615

Europe

Praxair Surface Technologies S.A.
25, rue de Veyrot
CH-1217 Meyrin
Geneva, Switzerland
Phone: +41 22 989 8989
Fax: +41 22 989 8913

Praxair Surface Technologies S.A.
Z.I. Molina la Chazotte
42 Allee J. Bigot - B.P. 688
42043 St. Etienne CEDEX 1
France
Phone: +33 4 77 42 6262
Fax: +33 4 77 42 6260

Praxair Surface Technologies S.p.A.
Via Fleming, 3
28100 Novara
Italy
Phone: +39 0321 674811
Fax: +39 0321 36691

Praxair Surface Technologies GmbH
Robert-Zapp-Strasse, 7
40880 Ratingen
Germany
Phone: +49 2102 495 200
Fax: +49 2102 495 219

Praxair Surface Technologies Ltd.
Drakes Way -Greenbridge Estate
Swindon, Wiltshire SN3 3HX
England, U.K.
Phone: +44 1793 512 555
Fax: +44 1793 611 608

Praxair Surface Technologies S.A.
Poligono Industrial "La Serra"
Carretera C 155 km 11,300
08185 Llica de Vall-Barcelona
Espana
Phone: +34 93 844 5742
Fax: +34 93 843 7523

Japan

Praxair Surface Technologies K.K.
1944-3, Shimoishido-Kami
Kitamoto-Shi, Saitama Pref.,364-0022
Japan
Phone: +81 48 591 0731
Fax: +81 48 592 3441

Praxair Surface Technologies KK.
580-18, Aza, Kosenouchi, Kuzaki
Kozuki-cho, Sayo-gun
Kyogo Pref., 679-5641
Japan
Phone: +81 790 88 0564
Fax: +81 790 88 0548

Brazil

Praxair Surface Technologies LTDA
Av. Maringa, 400
CEP 83324-010
Pinhais, PR, Brazil
Phone: +55 41 668 2211
Fax: +55 41 668 2442

Singapore

Asian Surface Technologies Pte.Ltd.
55 Loyang Drive
Singapore 508967
Phone: +65 6 545 8255
Fax: +65 6 542 8121

Praxair and the *Flowing Airstream* design are trademarks or registered trademarks of Praxair Technology, Inc., in the U.S. and in other countries.

D-Gun and *Super D-Gun* are trademarks or registered trademarks of Praxair S.T. Technologies, Inc. in the U.S. and in other countries