Devcon®

Technical Data Sheet

4/8/2009

HP 250 Q

Description: High performance epoxy with high shear strength and impact toughness for structural assembly applications.

Intended Use: Bonds metals, FRP/SMC composites,phenolics, stainless steel, aluminum, vinyl esters, nylon, PVC,PC,styrenics, wood, and rigid plastics.

Product features:
2/1 by volume
Easy to use
Room Temperature Cure
Excellent Chemical Resistance
Non Corrosive

Limitations: None

Typical Physical Properties:

Technical data should be considered representative or typical only and should not be used for specification purposes.

Cured 7 days @ 75° F	
Adhesive Lap Shear (ABS)	850 psi
Adhesive Lap Shear (Al)	2,475 psi
Adhesive Lap Shear (CRS)	2,600 psi
Adhesive Lap Shear (FRP)	1,875 psi
Adhesive Lap Shear (SS)	2,850 psi
Gap Fill	Excellent
Glass Transition Temp	82°C
Shore Hardness	78D
Side Impact (GBSS)	142 in-lb.
Solids by Volume	100
Tpeel	45 pli (Abraded Alumimum)

TESTS CONDUCTED

Adhesive Tensile Shear ASTM D 1002
Cured Hardness Shore D ASTM D 2240
T-Peel Strength ASTM D 1876

Uncured	
Color	Straw
Fixture Time	3 - 3.5 hours(Time to reach 50 psi in Lap Shear
Full Cure	3 days
Functional Cure	12 hrs. @ 72°F
Mix Ratio by Volume	2:1
Mix Ratio by Weight	100:44
Mixed Density	9.15 lbs./gal. : 1.10 gm/cc
Working Time	30 min. @ 72°F

Surface Preparation: Clean surface by solvent-wiping any deposits of heavy grease, oil, dirt, or other contaminants. Surface can also be cleaned with industrial cleaning equipment such as vapor phase degreasers or hot aqueous baths. If working with metal, abrade or roughen the surface to significantly increase the microscopic bond area and increase the bond strength.

Mixing Instructions: ---- Proper homogenous mixing of resin and hardener is essential for the curing and development of stated strengths. ----

25 ML DEV-TUBE
1. Squeeze material into a small container the size of an ashtray.
2. Using mixing stick included on Dev-tube handle, vigorously mix components for one (1) minute.
3. Immediately apply to substrate.

50 ML/400ML/490 ML CARTRIDGES
1. Attach cartridge to Mark V ™ [50ml] 400ml manual or pneumatic dispensing systems.
2. Open tip.
3. Burp cartridge by squeezing out some material until both sides are uniform (ensures no air bubbles are present during mixing).
4. Attach mix nozzle to end of cartridge.
5. Apply to substrate.

Application Instructions:

1. Apply mixed epoxy directly to one surface in an even film or as a bead.
2. Assemble with mating part within recommended working time.
3. Apply firm pressure between mating parts to minimize any gap and ensure good contact (a small fillet of epoxy should flow out the edges to display adequate gap fill.)

For very large gaps:
1. Apply epoxy to both surfaces
2. Spread to cover entire area OR make a bead pattern to allow flow throughout the joint

Let bonded assemblies stand for recommended functional cure time prior to handling.

-CURE SCHEDULE-
3 days @ 72°F. For ultimate chemical and thermal resistance, allow parts to cure overnight at room temperature, then follow with 2 hours of 80°C exposure.

Storage: Store in a cool, dry place.

Compliances: None

Chemical Resistance:

Chemical resistance is calculated with a 7 day, room temp. cure (30 days immersion) @ 75°F)

Acetic (Dilute) 10%	Excellent
Ammonia	Excellent
Cutting Oil	Excellent
Ethanol	Very good
Gasoline (Unleaded)	Excellent
Hydrochloric 10%	Excellent
Isopropanol	Very good
Mineral Spirits	Excellent

Motor Oil	Excellent
Sodium Hydroxide 10%	Very good
Sodium Hypochlorite	Excellent
Sulfuric 10%	Very good

Precautions: Please refer to the appropriate material safety data sheet (MSDS) prior to using this product.

For technical assistance, please call 1-800-933-8266

FOR INDUSTRIAL USE ONLY

Warranty: Devcon will replace any material found to be defective. Because the storage, handling and application of this material is beyond our control, we can accept no liability for the results obtained.

Disclaimer: All information on this data sheet is based on laboratory testing and is not intended for design purposes. ITW Devcon makes no representations or warranties of any kind concerning this data.

Order Information: **14417 400 ml cartridge**